

H-2Z - Thin Heat Shrink Tubes

ŚREDNICA PRZED
OBKURCZENIEM



Details:

- **Material:** Crosslinked polyolefin
- **Color:** black -BLK, yellow- YEL, blue -BLU, szary -GR, brown -BRW, green -GREEN, czerwony -RED, biały -WH, orange -OR
- **Operating temperature:** -55°C to +125°C
- **Min. shrink temperature:** 70°C
- **Min. full shrink temperature:** 100°C

Part No.	Size	Before heatshrink	After heatshrink		Spool length
		Min. diameter	Max. diameter	Min wall thickness	
	[inches]	[mm]			[m]
H-2Z-38.1	1 1/2	38.1	19.10	1.02	30

Własności	Test	Wynik testu
Temperatura pracy	UL 224	-55°C do ±125°C
Wytrzymałość	ASTM D 2671	>14MPa
Wydłużenie	ASTM D 2671	400%
Skurcz wzdłużny	UL 224	±5%
Mimośrodowość	ASTM D 2671	<30%
Starzenie cieplne	158°C/168 hrs	>12MPa >350%
Palność	VW-1	Niepalna
Wytrzymałość dielektryczna	IEC 243	>20kV/mm
Oporność skośna	ASTM D 2671	>10 ¹⁴ Ωcm
Zachowanie w kontakcie z Cu	UL 224	zaliczony