

H-2LS - Thin heat shrink tube



Details:

- **Material:** Crosslinked polyolefin
- **Color:** black
- **Operating temperature:** -45°C to +125°C
- **Min. shrink temperature:** 65°C
- **Min. full shrink temperature:** 95°C
- **Complies with:** RoHS, Sony-SS-00259
- **Recommended storage temperature below 40°C**

Part No	Size	Before heat shrink	After heat shrink		Spool
		Min. dia.	Max. dia	Min. wall thickness	
	[cal]	[mm]			[m]
H-2LS-50.8	2	50.8	25.4	1.1	50

Własności	Test	Wynik testu
Wytrzymałość	ASTM D 2671	>12MPa
Wydłużenie	ASTM D 2671	400%
Skurcz wzdłużny	UL 224	±5%
Mimośrodowość	ASTM D 2671	<30%
Starzenie cieplne	158°C/168 hrs	>11MPa >200%
Oporność skrośna	ASTM D 2671	>10 ¹⁴ Ωcm
Zachowanie w kontakcie z Cu	ASTM D 2671	zaliczony
Korozja Cu	UL 224	Nie powoduje