

H-2LS - Thin heat shrink tube



Details:

- **Material:** Crosslinked polyolefin
- **Color:** black
- **Operating temperature:** -45°C to +125°C
- **Min. shrink temperature:** 65°C
- **Min. full shrink temperature:** 95°C
- **Complies with:** RoHS, Sony-SS-00259
- **Recommended storage temperature below 40°C**

Symbol	Nominal diameter	Min. diameter before shrink	Max. diameter after shrink	Wall thickness	Length
	[in]	[mm]	[mm]	[mm]	[m]
H-2LS-12.7	1/2	12.7	6.4	0.6	50

Własności	Test	Wynik testu
Wytrzymałość	ASTM D 2671	>12MPa
Wydłużenie	ASTM D 2671	400%
Skurcz wzdłużny	UL 224	±5%
Mimośrodowość	ASTM D 2671	<30%
Starzenie cieplne	158°C/168 hrs	>11MPa >200%
Oporność skrośna	ASTM D 2671	>10 ¹⁴ Ωcm
Zachowanie w kontakcie z Cu	ASTM D 2671	zaliczony
Korozja Cu	UL 224	Nie powoduje